



TKF TESSUTO VELCRO ALUMINIZZATO

TKF adopts PET Scrim as reinforcement, coats aggressive solvent acrylic adhesive, and protected with 80gsm double-sided brown color silicone glassine paper.

TT8025G Tape is special designated for foam lamination. It is mainly for foam thermal insulation and cushion in air-conditioning / refrigeration / automobile industry.

TYPICAL PHYSICAL PROPERTIES

PROPERTIES	METRIC	ENGLISH	TEST METHOD
Total Thickness	80 Micron	3.2 Mil	PSTC-133 / ASTM D 3652
Adhesion to Steel	15 N/25mm	46.8 Oz./In.	PSTC-101 / ASTM D 3330
Tack Rolling Ball	10 cm	4.0 In.	PSTC-6 / ASTM D 3121
Tensile Strength	40 N/25mm	3.5 Lb/In	PSTC-131 / ASTM D 3759
Elongation	3.5 %	3.5 %	PSTC-131 / ASTM D 3759
Service Temperature	-20 ~ +100 °C	-4 ~ +212 °F	-----
Applying Temperature	+10 ~ 40 °C	+50 ~ +105 °F	-----

PRODUCT FORM & AVAILABLE SIZE

Log Roll: 1020mm x 45M / 50M

Jumbo Roll: 1020mm x 1000M / 500M / 250M

IMPORTANT NOTE

1. The data above are typical values only, and should not be used for specifications purpose.
2. Tolerance: Thickness: $\pm 10\%$; Width: $\pm 3\text{mm}$; Length: Cut Roll: $\pm 0.3\text{m}$, Jumbo Roll $\pm 0.5\%$.

STORAGE & SHELF LIFE:

12 months when stored at 21°C (70°F) / 50% relative humidity out of direct sunlight.

SUGGESTIONS FOR PRODUCT APPLICATION:

It is essential that the user evaluate the **Tecno Tape** product to determine whether it is fit for a particular purpose and user's method of application. Good results will be obtained when applied to a clean, dry surface with a suitable pressure on **Tecno Tape** products between +10 ~ +40°C (+50 ~ +105 °F).